# MSDS simalube SL24

Blasolube Lithium Komplexfett EPAQ 2

Dear simalube Customer,

We hereby confirm that the automatic lubricators simalube and simalube multipoint with the designation SL24 are filled with Blaser 04811-01 (Blasolube lithium complex grease) lubricant. The Material Safety Data Sheet (MSDS) for this lubricant is provided on the following pages. Please visit <u>www.simatec.com</u> for further technical data regarding this lubricant and simatec

### Werter simalube Kunde

Wir bestätigen hiermit, dass die automatischen Schmierstoffspender simalube und simalube multipoint, mit der Bezeichnung SL24, mit dem Schmierstoff Blaser 04811-01 (Blasolube lithium complex grease) befüllt sind. Das Sicherheitsdatenblatt zu diesem Schmierstoff finden Sie auf den folgenden Seiten. Technische Daten zum Schmierstoff und den automatischen Schmierstoffspendern simalube finden Sie unter: <u>www.simatec.com</u>

### Cher client simalube

Nous certifions que les graisseurs automatiques simalube et simalube multipoint appelés SL24 sont remplis avec le lubrifiant Blaser 04811-01 (Blasolube lithium complex grease). La fiche de données de sécurité de ce lubrifiant peut être trouvé dans les pages suivantes. Concernant les données techniques du lubrifiant tout comme les graisseurs automatiques simalube, vous allez trouver ces détails sous le lien suivant : www.simatec.com

### Estimado cliente de simalube

Por la presente certificamos que los lubricadores automáticos simalube y simalube multipoint con la designación SL24, están rellenados con el lubricante Blaser 04811-01 (Blasolube lithium complex grease). La ficha de datos de seguridad de este lubricante puede encontrar en la siguiente página. Para especificaciones técnicas del lubricante y de los lubricadores automáticos simalube ver:

### Caro cliente simalube

Con la presente confermiamo che i lubrificatori automatici simalube e simalube multipoint con la designazione SL24 sono riempiti con lubrificante Blaser 04811-01 (Blasolube lithium complex grease). La scheda dati di sicurezza per questo lubrificante é riportato sulle seguenti pagine. I dati tecnici

04.05.2020 / simatec ag, Wangen a. Aare, Switzerland

MSDS - simalube SL24



ES

FR

DE

EN



Revision: 04.05.2020

### Printing date 04.05.2020

Version number 4

SECTION 1: Identification of the substance/mixture and of the company/undertaking 1.1 Product identifier · Trade name: Blasolube® Lithium Complex Grease EPAQ 2 · Article number: 04811-01 1.2 Relevant identified uses of the substance or mixture and uses advised against No further relevant information available. · Application of the substance / the preparation: For industrial use only Lubricant Lubricating grease 1.3 Details of the supplier of the safety data sheet · Manufacturer / Supplier: BLASER SWISSLUBE AG Winterseistrasse 22 CH-3415 Hasle-Rüegsau Switzerland Tel.: +41 (0)34 460 01 01 E-mail: contact@blaser.com · Further information obtainable from: Product Safety Department E-mail: sds@blaser.com · 1.4 Emergency telephone number: Toxicological information Switzerland: 24-h-Emergency number: 145 (from abroad: +41 44 251 51 51) Information: +41 44 251 66 66 For advice on chemical emergencies, spillages, fires or exposures: +44 1235 239670 (24h/7d) **SECTION 2: Hazards identification** · 2.1 Classification of the substance or mixture: Classification according to Regulation (EC) No 1272/2008 Skin Sens. 1 H317 May cause an allergic skin reaction. 2.2 Label elements Labelling according to Regulation (EC) No 1272/2008 The product is classified and labelled according to the CLP regulation. Hazard pictograms



- · Signal word Warning
- Hazard-determining components of labelling: Naphthenic acids, zinc salts, basic Reaction products of bis(4-methylpentan-2-yl)dithiophosphoric acid with phosphorus oxide, propylene oxide and amines, C12-14-alkyl (branched)
- Hazard statements

H317 May cause an allergic skin reaction.

- · Precautionary statements
- P261 Avoid breathing dust/fume/gas/mist/vapours/spray.
- P280 Wear protective gloves.

P302+P352 IF ON SKIN: Wash with plenty of water.

- P362+P364 Take off contaminated clothing and wash it before reuse.
- P333+P313 If skin irritation or rash occurs: Get medical advice/attention.
- P501 Dispose of contents/container in accordance with local/regional/national/international regulations.

(Contd. on page 2)



Revision: 04.05.2020

# Printing date 04.05.2020

Version number 4

### Trade name: Blasolube® Lithium Complex Grease EPAQ 2

- · 2.3 Other hazards None
- · Results of PBT and vPvB assessment
- · PBT: Not applicable.
- · vPvB: Not applicable.

### **SECTION 3: Composition/information on ingredients**

### · 3.2 Mixtures

### · Description:

Mixture of substances listed below with nonhazardous additions. Mineral oil grease with a lithium complex soap as thickener.

<ul> <li>Declarable, or hazardous of CAS-no.</li> </ul>	components:	
CAS: 38900-29-7 EINECS: 254-184-4 Reg.nr.: 01-2120119814-57	Dilithium azelate Acute Tox. 4, H302	>1-6.9%
CAS: 84418-50-8 EINECS: 282-762-6 Reg.nr.: 01-2119988500-34	Naphthenic acids, zinc salts, basic Eye Irrit. 2, H319; Skin Sens. 1, H317; Aquatic Chronic 3, H412	>1-2.9%
EC number: 931-384-6 Reg.nr.: 01-2119493620-38	Reaction products of bis(4-methylpentan-2-yl)dithiophosphoric acid with phosphorus oxide, propylene oxide and amines, C12-14-alkyl (branched) Eye Dam. 1, H318; Aquatic Chronic 2, H411; Acute Tox. 4, H302; Skin Sens. 1, H317	<0.25%

**Additional information:** For the wording of the listed hazard phrases refer to section 16.

### **SECTION 4: First aid measures**

### 4.1 Description of first aid measures

- · General information: Immediately remove any clothing soiled by the product.
- · After inhalation:
- Supply fresh air and to be sure call for a doctor.

In case of unconsciousness place patient stably in side position for transportation.

- Not applicable, as the concentrate is not volatile.
- After skin contact: Immediately wash with water and soap and rinse thoroughly.
- After eye contact: Rinse opened eye for several minutes under running water.
- · After swallowing: If symptoms persist consult doctor.
- 4.2 Most important symptoms and effects, both acute and delayed No further relevant information available.
- 4.3 Indication of any immediate medical attention and special treatment needed
- No further relevant information available.

### **SECTION 5: Firefighting measures**

- 5.1 Extinguishing media
- Suitable extinguishing agents: CO<sub>2</sub>, powder or water spray. Fight larger fires with water spray.
- For safety reasons unsuitable extinguishing agents: Water with full jet
- 5.2 Special hazards arising from the substance or mixture No further relevant information available.
- · 5.3 Advice for firefighters
- · Protective equipment: No special measures required.
- · Additional information Cool endangered receptacles with water spray.

### **SECTION 6: Accidental release measures**

• 6.1 Personal precautions, protective equipment and emergency procedures Not required.

• 6.2 Environmental precautions: Do not allow to enter sewers/ surface or ground water.

(Contd. of page 1)



Revision: 04.05.2020

(Contd. of page 2)

# Printing date 04.05.2020

Version number 4

### Trade name: Blasolube® Lithium Complex Grease EPAQ 2

- 6.3 Methods and material for containment and cleaning up: Dispose contaminated material as waste according to item 13. Ensure adequate ventilation.
   6.4 Reference to other sections
- See Section 7 for information on safe handling. See Section 8 for information on personal protection equipment. See Section 13 for disposal information.

### **SECTION 7: Handling and storage**

· 7.1 Precautions for safe handling

Ensure good ventilation/exhaustion at the workplace. The product has been classified and marked in accordance with EU Directives / Ordinance on Hazardous Materials.

- Observe the general safety regulations when handling chemicals.
- · Information about fire and explosion protection: No special measures required.
- · 7.2 Conditions for safe storage, including any incompatibilities
- · Storage:
- Requirements to be met by storerooms and receptacles: Store only in the original receptacle.
- Information about storage in one common storage facility: Store away from oxidising agents.
- · Further information about storage conditions:

Protect from heat and direct sunlight.

Optimal storage temperature between 0°C and 40°C.

Duration of storage: In original container, at least 3 years.

· 7.3 Specific end use(s) No further relevant information available.

### **SECTION 8: Exposure controls/personal protection**

• Additional information about design of technical facilities: No further data; see item 7.

- · 8.1 Control parameters
- · Ingredients with limit values at the workplace: TLV value (oil mist) CH: 5 mg/m<sup>3</sup>
- · Additional information: The lists valid during the making were used as basis.
- · 8.2 Exposure controls
- Personal protective equipment:
- General protective and hygienic measures: Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work.
- · Respiratory protection: Not required.
- Protection of hands:



Protective gloves

The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture.

Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation **Material of gloves** 

The selected protective gloves have to satisfy the specifications of EU Directive 89/686/EEC and the resultant standard EN 374.

The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer.

The break through, among others, depending on material density and the type of glove and therefore must be determined in each individual case.

Gloves must be inspected prior to use. Replace when worn!

Impervious gloves: nitrile rubber, minimum thickness of 0.3 mm.

(Contd. on page 4)

Printing date 04.05.2020

Safety Data Sheet according to 1907/2006/EC, Article 31 and 830/2015/EC

Version number 4



Revision: 04.05.2020

(Contd. of page 3)

## Trade name: Blasolube® Lithium Complex Grease EPAQ 2

### · Penetration time of glove material

- The exact breaktrough time has to be found out by the manufacturer of the protective gloves and has to be observed.
- Eye protection: Eye protector with side protection (framed eyeglasses) EN 166.
- · Body protection: Protective work clothing

<ul> <li>9.1 Information on basic physical and chemical properties</li> <li>General Information</li> <li>Appearance: Form: Pasty Colour: Light yellow Odour: Mineral-oil-like Odour threshold: Not determined.</li> <li>PH-value: Not applicable.</li> <li>Change in condition: Metting point/freezing point: Not applicable Initial boiling range: Not determined.</li> <li>Drip point: &gt;280 °C (ISO 2176 / ASTM D566) Pour point: Not determined.</li> <li>Flash point: &gt;150 °C (ISO 2592 / ASTM D92)</li> <li>Flash point: &gt;150 °C (ISO 2592 / ASTM D92)</li> <li>Flash point: &gt;350 °C (ISO 2592 / ASTM D92)</li> <li>Flash point: &gt;350 °C (ISO 2592 / ASTM D92)</li> <li>Flash point: &gt;350 °C (ISO 2592 / ASTM D92)</li> <li>Explosition temperature: &gt;350 °C</li> <li>Auto-ignition temperature: Product is not selfigniting.</li> <li>Explosion limits (@1013 mbar): Lower: Not determined.</li> <li>Oxidising properties Not applicable.</li> <li>Out ignition geneties Not applicable.</li> <li>Out officiang of C: 0.95 g/cm° (DIN 51757 / ASTM D1217)</li> <li>Vapour density Not applicable.</li> <li>Evaporation rate Not applicable.</li> <li>Evaporation rate Not applicable.</li> <li>Solubility in / Miscibility with water: Insoluble.</li> <li>Partition coefficient: n-octanol/water: Not applicable.</li> <li>Viscosity: Dynamic: Not applicable.</li> <li>VOC (CH): 0.0</li> <li>9.2 Other information: safety relevant data, which has to be considered as product specificable.</li> </ul>	SECTION 9: Physical and chemical	properties
Appearance: Form:Pasty Colour:Dasty Light yellow Odour:Colour:Light yellow Mineral-oil-like Odour threshold:Not determined.PH-value:Not applicable.• Change in condition: Metting point/reezing point:Not applicable• Initial boiling range:Not determined.Drip point: Pour point:>280 °C (ISO 2176 / ASTM D566) Pour point:• Flash point: Initial boiling ags):Not determined.• Flash point: up to int: Pour point:>350 °C (ISO 2592 / ASTM D92)• Flamability (solid, gas): up to int applicable.Not applicable.• Flash point: up to int: up to int applicable.>350 °C• Clino temperature: up to int applicable.>350 °C• Explosive properties: upper:Product is not selfigniting.• Explosive properties: upper:Not determined.• Upper: variant applicable.Not applicable.• Oxidising properties: variant applicable.Not applicable.• Density at 20 °C: vapour density water:0,95 g/cm² (DIN 51757 / ASTM D1217)• Vapour density water:Not applicable.• Solubility in / Miscibility with water:Not applicable.• Partition coefficient: n-octanol/waterNot applicable.• Viscosity: Dynamic: kinematic: PenetrationNot applicable.• Voc (CH):0.00.0		hemical properties
Form:Pasty Light yellow Odour:Light yellow Light yellow Odour:Odour:Mineral-oil-like Odour threshold:Not determined.pH-value:Not applicable.• Change in condition:Mot applicable Initial point/recript point:Metting point/recript point:Not applicable Pour point:Initial boiling point and boiling range:Not determined.Prip point:>280 °C (ISO 2176 / ASTM D566) Pour point:Pour point:Not determinedFlash point:>150 °C (ISO 2592 / ASTM D92)Flammability (solid, gas):Not applicable.Ignition temperature:>350 °C (DIN 51794 / ASTM E659)• Decomposition temperature:>350 °C• Auto-ignition temperature:>350 °C• Auto-ignition temperature:>350 °C• Change rightProduct is not selfigniting.• Explosion limits (@1013 mbar):Implicable.• Lower:Not determined.• Upper:Not determined.• Oxidising propertiesNot applicable.• Density at 20 °C:0.95 g/cm³ (DIN 51757 / ASTM D1217)• Vapour densityNot applicable.• Solubility in / Miscibility with water:Insoluble.• Partition coefficient: n-octanol/water:Not determined.• Viscosity:Dynamic: Not applicable.• Dynamic:Not applicable.• Voc (CH):0.0	_	
Colour:Light yellowOdour:Mineral-oil-likeOdour threshold:Not determined.PH-value:Not applicable.Change in condition: Metting point/freezing point: Initial boiling noin and boiling range: Not determined.Not applicableDrip point: Pour point:>280 °C (ISO 2176 / ASTM D566) Pour point: Initial boiling ags):Not determined.Flash point: (solid, gas):>150 °C (ISO 2592 / ASTM D92)Flammability (solid, gas): (solid, gas):Not applicable.Jepticable. (aprition temperature: vost (2013 mbar): Lower: Upper:>350 °CAuto-ignition temperature: vost determined.>350 °CProduct is not selfigniting.Explosion limits (@1013 mbar): Lower: Vot determined.Upper: Vapour density water:Not determined.Oxidising properties0.95 g/cm³ (DIN 51757 / ASTM D1217) Not applicable.Vapour density water:Insoluble.Partition coefficient: n-octanol/water: Viscosity: Dynamic: Kinematic: Penetration 265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2VOC (CH):0.0	• •	
Odour:Mineral-oil-like Not determined.odour threshold:Not determined.• pH-value:Not applicable.Change in condition: Metting point/freezing point: Initial boiling point and boiling range: SPOUP point:Not applicable SPOUP point: SPOUP point:Pour point:>280 °C (ISO 2592 / ASTM D566) Pour point: >350 °C (ISO 2592 / ASTM D92)Flash point:>150 °C (ISO 2592 / ASTM D92)Flammability (solid, gas): Ignition temperature: Solo °C (ISO 2592 / ASTM E659)Decomposition temperature: Solo °C (DIN 51794 / ASTM E659)Decomposition temperature: Vover: Upper: Not determined.Faplosive properties: Upper: Not determined.Vode does not present an explosion hazard.Explosion limits (@1013 mbar): Lower: Upper: Not determined.Lower: Upper: Not determined.Oxidising propertiesNot determined.Oxidising propertiesNot determined.Vapour density water:Insoluble.Partition coefficient: n-octanol/water: Voscisty: Dynamic: Not applicable.Partition coefficient: n-octanol/water: Not applicable.Viscosity: Dynamic: RenetrationVosc (CH):0.0		
Odour threshold:Not determined.pH-value:Not applicable.Change in condition:Not applicableInitial boiling point:Not applicableInitial boiling point:Not applicableInitial boiling point:>280 °C (ISO 2176 / ASTM D566)Pour point:>280 °C (ISO 2592 / ASTM D92)Flash point:>150 °C (ISO 2592 / ASTM D92)Flash point:>350 °C (DIN 51794 / ASTM E659)Ignition temperature:>350 °CAuto-ignition temperature:>350 °CAuto-ignition temperature:>350 °CExplosive properties:Product is not selfigniting.Explosion limits (@1013 mbar):Not determined.Lower:Not determined.Upper:Not determined.Oxidising propertiesNot determined.Oxidising propertiesNot applicable.Ponsity at 20 °C:0.95 g/cm (DIN 51757 / ASTM D1217)Not applicable.Not applicable.Posity if / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not applicable.Portition coefficient: n-octanol/water:Not applicable.Viscosity: Dynamic: Kinematic:Not applicable.VOC (CH):0.0		
pH-value:       Not applicable.         Change in condition: Melting point/freezing point: Initial boiling point and boiling range: Not determined.       Not applicable Not determined.         Drip point: Pour point:       >280 °C (ISO 2176 / ASTM D566) Not determined         Flash point:       >150 °C (ISO 2592 / ASTM D92)         Flammability (solid, gas):       Not applicable.         Ignition temperature:       >350 °C         Auto-ignition temperature:       >350 °C         Auto-ignition temperature:       Product is not selfigniting.         Explosive properties:       Product does not present an explosion hazard.         Explosion limits (@1013 mbar): Lower:       Not determined.         Upper:       Not determined.         Voger:       Not determined.         Vapport density       Not applicable.         • Density at 20 °C:       0.95 g/cm³ (DIN 51757 / ASTM D1217)         Vapour density       Not applicable.         • Solubility in / Miscibility with water:       Insoluble.         Partition coefficient: n-octanol/water:       Not applicable.         Viscosity:       Dynamic: Parentration       Not applicable.         Voc (CH):       0.0		
Change in condition:       Not applicable         Melting point/freezing point:       Not applicable         Initial boiling point and boiling range:       Not determined.         Drip point:       >280 °C (ISO 2176 / ASTM D566)         Pour point:       >150 °C (ISO 2592 / ASTM D92)         Flash point:       >150 °C (ISO 2592 / ASTM D92)         Flammability (solid, gas):       Not applicable.         Ignition temperature:       >350 °C (DIN 51794 / ASTM E659)         Decomposition temperature:       >350 °C         Auto-ignition temperature:       Product is not selfigniting.         Explosive properties:       Product does not present an explosion hazard.         Explosion limits (@1013 mbar):       Lower:         Lower:       Not applicable.         Upper:       Not determined.         Vot applicable.       Not applicable.         Oxidising properties       Not determined.         Vapor density       Not applicable.         Vapor density       Not applicable.         Solubility in / Miscibility with       Metermined.         Water:       Insoluble.         Partition coefficient: n-octanol/water:       Not determined.         Viscosity:       Dynamic:       Not applicable.         Pontition coefficient: n-octanol	Odour threshold:	Not determined.
Melting point/freezing point: Initial boiling point and boiling range: Not determined. Pour point:Not applicable Not determined.Prip point: Pour point:>280 °C (ISO 2592 / ASTM D566) Not determinedFlash point:>150 °C (ISO 2592 / ASTM D92)Flammability (solid, gas): Ignition temperature:Not applicable. >350 °C (DIN 51794 / ASTM E659)Decomposition temperature: Ignition temperature:>350 °CAuto-ignition temperature: Lower: Upper:Product does not present an explosion hazard.Explosion limits (@1013 mbar): Lower: Upper: Not determined.Not determined.Oxidising properties:Not determined.• Oxidising properties:Not determined.• Oxidising properties:0.95 g/cm³ (DIN 51757 / ASTM D1217)• Vapour density water:Not applicable.• Solubility in / Miscibility with water:Insoluble.• Partition coefficient: n-octanol/water: Not applicable.Not determined.• Viscosity: Dynamic: Kinematic: Penetration 265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2Not• VOC (CH):0.0	pH-value:	Not applicable.
Initial boiling point and boiling range:Not determined.Drip point:>280 °C (ISO 2176 / ASTM D566)Pour point:Not determinedFlash point:>150 °C (ISO 2592 / ASTM D92)Flash point:>350 °C (ISO 2592 / ASTM E659)Ignition temperature:>350 °CAuto-ignition temperature:>350 °CAuto-ignition temperature:>350 °CAuto-ignition temperature:>350 °CAuto-ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Explosion limits (@1013 mbar):Not determined.Lower:Not determined.Oxidising propertiesNot applicable.Oxidising properties0.95 g/cm³ (DIN 51757 / ASTM D1217)Vapour densityNot applicable.Not determined.Not determined.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity: Dynamic: Kinematic:Not applicable. Not applicable.Viscosity: Dynamic: Kinematic:Not applicable. Not applicable.VOC (CH):0.0		
Drip point:>280 °C (ISO 2176 / ASTM D566) Not determinedPour point:>150 °C (ISO 2592 / ASTM D92)Flammability (solid, gas):Not applicable.Ignition temperature:>350 °CDecomposition temperature:>350 °CAuto-ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Explosion limits (@1013 mbar): Lower:Not determined.Upper:Not determined.Upper:Not determined.Oxidising properties0.95 g/cm³ (DIN 51757 / ASTM D1217)Vapour densityNot applicable.Evaporation rateNot applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not applicable.Viscosity: Dynamic: Kinematic:Not applicable.VOC (CH):0.0		
Pour point:Not determinedFlash point:>150 °C (ISO 2592 / ASTM D92)Flammability (solid, gas):Not applicable.Ignition temperature:>350 °C (DIN 51794 / ASTM E659)Decomposition temperature:>350 °CAuto-ignition temperature:>350 °CAuto-ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Explosion limits (@1013 mbar): Lower: Upper:Not determined.Vot determined.Not determined.Oxidising propertiesNot applicable.Density at 20 °C:0.95 g/cm³ (DIN 51757 / ASTM D1217)Vapour densityNot applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity: Dynamic: Kinematic:Not applicable. Not applicable.VOC (CH):0.0		
Flash point:>150 °C (ISO 2592 / ASTM D92)Flammability (solid, gas):Not applicable.Ignition temperature:>350 °C (DIN 51794 / ASTM E659)Decomposition temperature:>350 °CAuto-ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Explosion limits (@1013 mbar):Lower:Lower:Not determined.Upper:Not determined.Oxidising properties0.95 g/cm³ (DIN 51757 / ASTM D1217)Vapour densityNot applicable.Evaporation rateNot applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity: Dynamic: Kinematic:Not applicable.VOC (CH):0.0		>280 °C (ISO 2176 / ASTM D566)
Flammability (solid, gas): Ignition temperature:Not applicable. >350 °C (DIN 51794 / ASTM E659)Decomposition temperature:>350 °CAuto-ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Explosion limits (@1013 mbar): Lower: Upper:Not determined. 0.95 g/cm³ (DIN 51757 / ASTM D1217)Vapour densityNot applicable. Not applicable.Evaporation rateNot applicable. Not applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not applicable. Not applicable.Viscosity: Dynamic: Kinematic: PenetrationNot applicable. Not applicable. Not applicable.VOC (CH):0.0	Pour point:	Not determined
Ignition temperature:>350 °C (DIN 51794 / ASTM E659)Decomposition temperature:>350 °CAuto-ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Explosion limits (@1013 mbar):Image: Composition temperature:Lower:Not determined.Upper:Not determined.Oxidising propertiesNot applicable.Density at 20 °C:0.95 g/cm³ (DIN 51757 / ASTM D1217)Vapour densityNot applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity:Not applicable. Not applicable.Voscity:Not applicable. Not applicable.Viscosity:Insoluble.Dynamic:Not applicable. Not applicable.Viscosity:Not applicable. Not applicable.Viscosity:Not applicable. Not applicable.Viscosity:Not applicable. Not applicable.Viscosity:Not applicable. Not applicable.Viscosity:Not applicable. Not applicable. Not applicable.Vost (CH):0.0	Flash point:	>150 °C (ISO 2592 / ASTM D92)
Ignition temperature:>350 °C (DIN 51794 / ASTM E659)Decomposition temperature:>350 °CAuto-ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Explosion limits (@1013 mbar):Image: Composition temperature:Lower:Not determined.Upper:Not determined.Oxidising propertiesNot applicable.Density at 20 °C:0.95 g/cm³ (DIN 51757 / ASTM D1217)Vapour densityNot applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity:Not applicable. Not applicable.Voscity:Not applicable. Not applicable.Viscosity:Insoluble.Dynamic:Not applicable. Not applicable.Viscosity:Not applicable. Not applicable.Viscosity:Not applicable. Not applicable.Viscosity:Not applicable. Not applicable.Viscosity:Not applicable. Not applicable.Viscosity:Not applicable. Not applicable. Not applicable.Vost (CH):0.0	Flammability (solid, gas):	Not applicable.
Decomposition temperature:>350 °CAuto-ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Explosion limits (@1013 mbar):Image: Composition temperature:Lower:Not determined.Upper:Not determined.Oxidising propertiesNot applicable.Density at 20 °C:0.95 g/cm³ (DIN 51757 / ASTM D1217)Vapour densityNot applicable.Evaporation rateNot determined.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not applicable. Not applicable.Viscosity: Dynamic: Rinematic:Not applicable. Not applicable.Penetration265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2VOC (CH):0.0	Ignition temperature:	
Auto-ignition temperature:Product is not selfigniting.Explosive properties:Product does not present an explosion hazard.Explosion limits (@1013 mbar):Not does not present an explosion hazard.Lower:Not determined.Upper:Not determined.Oxidising propertiesNot applicable.Density at 20 °C:0.95 g/cm³ (DIN 51757 / ASTM D1217)Vapour densityNot applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not applicable.Viscosity: Dynamic: Kinematic: PenetrationNot applicable. Rot applicable.VOC (CH):0.0		
Explosive properties:Product does not present an explosion hazard.Explosion limits (@1013 mbar): Lower:Not determined.Dower:Not determined.Upper:Not determined.Oxidising propertiesNot applicable.Density at 20 °C:0.95 g/cm³ (DIN 51757 / ASTM D1217)Vapour densityNot applicable. Not determined.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity: Punamic: Rinematic:Not applicable. Not applicable. Not applicable.VOC (CH):0.0	· ·	
Explosion limits (@1013 mbar):       Not determined.         Lower:       Not determined.         Upper:       Not determined.         Oxidising properties       Not applicable.         Density at 20 °C:       0.95 g/cm³ (DIN 51757 / ASTM D1217)         Vapour density       Not applicable.         Not determined.       Not applicable.         Evaporation rate       Not applicable.         Solubility in / Miscibility with water:       Insoluble.         Partition coefficient: n-octanol/water:       Not determined.         Viscosity:       Not applicable.         Dynamic:       Not applicable.         Kinematic:       Not applicable.         Penetration       265 - 295 mm/10 @ 25°C (77°F) ASTM D 217         NLGI class: 2       VOC (CH):		
Lower: Upper:Not determined.Upper:Not determined.Oxidising propertiesNot applicable.Density at 20 °C:0.95 g/cm° (DIN 51757 / ASTM D1217)Vapour densityNot applicable. Not determined.Evaporation rateNot applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity: Dynamic: Kinematic:Not applicable. Not applicable.Viscosity: PenetrationNot applicable. 265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2VOC (CH):0.0	· · · ·	
Upper:Not determined.Oxidising propertiesNot applicable.• Density at 20 °C:0.95 g/cm³ (DIN 51757 / ASTM D1217)• Vapour densityNot applicable. Not determined.• Evaporation rateNot applicable.• Solubility in / Miscibility with water:Insoluble.• Partition coefficient: n-octanol/water:Not determined.• Viscosity: Dynamic: Kinematic:Not applicable. Not applicable.• Viscosity: PenetrationNot applicable. 265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2• VOC (CH):0.0		Not determined
• Oxidising properties       Not applicable.         • Density at 20 °C:       0.95 g/cm³ (DIN 51757 / ASTM D1217)         • Vapour density       Not applicable.         • Not determined.       Not applicable.         • Evaporation rate       Not applicable.         • Solubility in / Miscibility with water:       Insoluble.         • Partition coefficient: n-octanol/water:       Not determined.         • Viscosity:       Dynamic:         Dynamic:       Not applicable.         • Kinematic:       Not applicable.         Penetration       265 - 295 mm/10 @ 25°C (77°F) ASTM D 217         NLGI class: 2       0.0		
Density at 20 °C:       0.95 g/cm³ (DIN 51757 / ASTM D1217)         Vapour density       Not applicable.         Not determined.       Not applicable.         • Evaporation rate       Not applicable.         • Solubility in / Miscibility with water:       Insoluble.         • Partition coefficient: n-octanol/water:       Not determined.         • Viscosity:       Dynamic:         Dynamic:       Not applicable.         • Kinematic:       Not applicable.         Penetration       265 - 295 mm/10 @ 25°C (77°F) ASTM D 217         NLGI class: 2       0.0	• •	
Vapour densityNot applicable. Not determined. Not applicable.Evaporation rateNot applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity: Dynamic: Kinematic: PenetrationNot applicable. Not applicable. Not applicable. Not applicable. Not applicable. Not applicable. Not applicable. 0.0VOC (CH):0.0		
Not determined.Evaporation rateNot applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity: Dynamic: Kinematic: PenetrationNot applicable. 265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2VOC (CH):0.0		
Evaporation rateNot applicable.Solubility in / Miscibility with water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity: Dynamic: Kinematic: PenetrationNot applicable. 265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2VOC (CH):0.0	Vapour density	
Solubility in / Miscibility with water:       Insoluble.         Partition coefficient: n-octanol/water:       Not determined.         Viscosity:       Dynamic:         Dynamic:       Not applicable.         Kinematic:       Not applicable.         Penetration       265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2         VOC (CH):       0.0		
water:Insoluble.Partition coefficient: n-octanol/water:Not determined.Viscosity:Not applicable.Dynamic:Not applicable.Penetration265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2VOC (CH):0.0	Evaporation rate	Not applicable.
• Partition coefficient: n-octanol/water:       Not determined.         • Viscosity:       Dynamic:         Dynamic:       Not applicable.         Kinematic:       Not applicable.         Penetration       265 - 295 mm/10 @ 25°C (77°F) ASTM D 217         VOC (CH):       0.0	Solubility in / Miscibility with	
Viscosity:Dynamic:Not applicable.Kinematic:Not applicable.Penetration265 - 295 mm/10 @ 25°C (77°F) ASTM D 217NLGI class: 20.0	water:	Insoluble.
Dynamic:Not applicable.Kinematic:Not applicable.Penetration265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2VOC (CH):0.0	Partition coefficient: n-octanol/water:	Not determined.
Kinematic:Not applicable.Penetration265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2VOC (CH):0.0	Viscosity:	
Kinematic:Not applicable.Penetration265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2VOC (CH):0.0	Dynamic:	Not applicable.
Penetration         265 - 295 mm/10 @ 25°C (77°F) ASTM D 217 NLGI class: 2           VOC (CH):         0.0		
NLGI class: 2         VOC (CH):         0.0		
0.2 Other information of the considered as module an additional data which has to be considered as module as additional data which has to be considered as module as a difference of the construction of the c	VOC (CH):	0.0
• 3.2 VILEE INFORMATION: SALEN LEIEVAN DATA, WHICH HAS TO BE CONSIDERED AS DROUGT SPECIFICATIO		

### SECTION 10: Stability and reactivity

 $\cdot$  10.1 Reactivity None known if used as directed.

(Contd. on page 5)

EU -



Revision: 04.05.2020

Printing date 04.05.2020

Version number 4

### Trade name: Blasolube® Lithium Complex Grease EPAQ 2

- 10.2 Chemical stability Stable under recommended storage conditions.
- $\cdot$  10.3 Possibility of hazardous reactions Reacts with strong oxidising agents.
- **10.4 Conditions to avoid** No further relevant information available.
- · 10.5 Incompatible materials: No further relevant information available.
- · 10.6 Hazardous decomposition products: Carbon monoxide and carbon dioxide

### **SECTION 11: Toxicological information**

- · 11.1 Information on toxicological effects
- · Acute toxicity Based on available data, the classification criteria are not met.

### · LD/LC50 values relevant for classification:

### **ATE (Acute Toxicity Estimates)**

Oral LD50 10,000-20,000 mg/kg

# Reaction products of bis(4-methylpentan-2-yl)dithiophosphoric acid with phosphorus oxide, propylene oxide and amines, C12-14-alkyl (branched)

Oral LD50 >2,000 mg/kg (rat)

Dermal LD50 >2,000 mg/kg (rabbit)

### · Primary irritant effect:

- · Skin corrosion/irritation Based on available data, the classification criteria are not met.
- · Serious eye damage/irritation Based on available data, the classification criteria are not met.
- Respiratory or skin sensitisation
- May cause an allergic skin reaction.
- · Germ cell mutagenicity Based on available data, the classification criteria are not met.
- · Carcinogenicity Based on available data, the classification criteria are not met.
- · Reproductive toxicity Based on available data, the classification criteria are not met.
- · STOT-single exposure Based on available data, the classification criteria are not met.
- $\cdot$  STOT-repeated exposure Based on available data, the classification criteria are not met.
- $\cdot$  Aspiration hazard Based on available data, the classification criteria are not met.

### **SECTION 12: Ecological information**

- · 12.1 Toxicity
- · Aquatic toxicity: No further relevant information available.
- · 12.2 Persistence and degradability No further relevant information available.
- · 12.3 Bioaccumulative potential No further relevant information available.
- 12.4 Mobility in soil No further relevant information available.
- Additional ecological information:
- · General notes: Do not allow product to reach ground water, water course or sewage system.
- · 12.5 Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- · vPvB: Not applicable.
- 12.6 Other adverse effects No further relevant information available.

### **SECTION 13: Disposal considerations**

### · 13.1 Waste treatment methods

### · Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

### · European waste catalogue

12 01 12\* spent waxes and fats

### 13 08 99\* wastes not otherwise specified

(Contd. on page 6)

(Contd. of page 4)

Version number 4



Revision: 04.05.2020

(Contd. of page 5)

# Trade name: Blasolube® Lithium Complex Grease EPAQ 2

· Uncleaned packaging:

Printing date 04.05.2020

• **Recommendation:** Disposal must be made according to official regulations.

14.1 UN-Number ADR, ADN, IMDG, IATA	Not regulated
ADR, ADN, IMDG, IATA	Not regulated
14.2 UN proper shipping name	
ADR, ADN, IMDG, IATA	Not regulated
14.3 Transport hazard class(es)	
ADR, ADN, IMDG, IATA	
Class	Not regulated
14.4 Packing group	
ADR, IMDG, IATA	Not regulated
14.5 Environmental hazards:	
Marine pollutant:	No
14.6 Special precautions for user	Not applicable.
14.7 Transport in bulk according to Annex II	of Marpol
and the IBC Code	Not applicable.
Transport/Additional information:	Not dangerous according to the above specifications.
IATA	IATA Dangerous Goods Regulation (DGR): latest edition
UN "Model Regulation":	Not regulated

### **SECTION 15: Regulatory information**

- · 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- · Labelling according to Regulation (EC) No 1272/2008: CLP/GHS label elements are issued under section 2.
- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients are listed.

### · LIST OF SUBSTANCES SUBJECT TO AUTHORISATION (ANNEX XIV)

None of the ingredients are listed.

### · National regulations:

The product is subject to be labeled according with the prevailing version of the regulations on hazardous substances.

· Waterhazard class: Water hazard class 1 (Self-assessment): slightly hazardous for water.

Other regulations, limitations and prohibitive regulations
 Substances of very high concern (SVHC) according to REACH, Article 57
 This preparation does not contain any SVHC ("Substances of Very High Concern")

· 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

### **SECTION 16: Other information**

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

(Contd. on page 7)

- EU



Revision: 04.05.2020

(Contd. of page 6)

# Printing date 04.05.2020

Version number 4

### Trade name: Blasolube® Lithium Complex Grease EPAQ 2

### · Regulations / approvals / listings:

Information on REACH registration numbers in section 3:

If no REACH registration numbers on substances in section 3 are mentioned, then they are exempt from the REACH registration requirements (e.g. polymers).

### · RoHS:

The product is compliant with European Directives 2015/863/EC, 2011/65/EC, 2002/95/EC, WEEE 2002/96/EC, 2003/11/EC, 2005/53/EC and RoHS.

The following substances ARE NOT contained:

Pentabromodiphenylether, Octabromodiphenylether, polybrominated diphenylether (PBDE) and / or polybrominated biphenyls (PBB), Bis(2-ethylhexyl)phthalate (DEHP), Benzylbutylphthalate (BBP), Dibutylphthalate (DBP), Disobutylphthalate (DIBP);

lead or it's compounds, cadmium or it's compounds, mercury or it's compounds, chromium Cr<sup>6</sup>+-compounds.

### · IP346:

The contained refined mineral oils are exempt of labelling.

The content of polycyclic aromatic hydrocarbons (PCA) according to IP346 is < 3% (DMSO-extract).

### International Approvals:

TSCA (Toxic Substances Control Act, United States): all substances are registered and have CAS numbers.

### · TSE/BSE:

This product adheres to the standards of TSE/BSE-free products, according to European Community directives 93/42/ EEC and 2003/32/EC.

Materials and/or synthetically modified materials which are of animal origin from bovine, ovine, goats, cats, dogs, deer, elk and/or mink, are NOT included in this product.

This product is entirely free from latex containing materials.

### · Department issuing SDS: Product Stewardship

· Contact: Mrs. Wilson + Mr. Feller

### · Editor's notice:

The above mentioned data correspond to our present state of knowledge and experience. The safety data sheet serves as description of the products in regard to necessary safety measures. The indications have not the meaning of guarantees on properties.

### · Abbreviations and acronyms:

ICAO: International Civil Aviation Organisation

RoHS: Restriction of Hazardous Substances

ADR: Accord européen sur le transport des marchandises dangereuses par Route (European Agreement concerning the International Carriage of Dangerous Goods by Road)

RID: Règlement international concernant le transport des marchandises dangereuses par chemin de fer (Regulations Concerning the International Transport of Dangerous Goods by Rail)

IMDG: International Maritime Code for Dangerous Goods

IATA: International Air Transport Association

GHS: Globally Harmonised System of Classification and Labelling of Chemicals EINECS: European Inventory of Existing Commercial Chemical Substances

ELINCS: European List of Notified Chemical Substances

CAS: Chemical Abstracts Service (division of the American Chemical Society)

VOC: Volatile Organic Compounds (USA, EU)

ISO: International Organisation for Standardisation

DNEL: Derived No-Effect Level (REACH) PNEC: Predicted No-Effect Concentration (REACH)

LC50: Lethal concentration, 50 percent

LD50: Lethal dose, 50 percent

PBT: Persistent, Bioaccumulative and Toxic

NIOSH: National Institute for Occupational Safety

OSHA: Occupational Safety & Health

TLV: Threshold Limit Value

PEL: Permissible Exposure Limit REL: Recommended Exposure Limit

ATE: Acute Toxicity Estimate

Acute Tox. 4: Acute toxicity - oral - Category 4

Eye Dam. 1: Serious eye damage/eye irritation – Category 1

Eye Irrit. 2: Serious eye damage/eye irritation – Category 2

Skin Sens. 1: Skin sensitisation – Category 1

Aquatic Chronic 2: Hazardous to the aquatic environment - long-term aquatic hazard - Category 2 Aquatic Chronic 3: Hazardous to the aquatic environment - long-term aquatic hazard - Category 3

EU -

Printing date 04.05.2020

Safety Data Sheet according to 1907/2006/EC, Article 31 and 830/2015/EC

Version number 4



Revision: 04.05.2020

# Trade name: Blasolube® Lithium Complex Grease EPAQ 2

 $\cdot$  \* Data compared to the previous version altered.

The asterisk (\*) on the left side indicate the respective changes from the previous version.

(Contd. of page 7)

EU -